

## TUNFLUID HTG 220

High-temperature synthetic oil for lubricating IS hollow glass machines

### Benefits

- ✓ Excellent wear protection for reliable machine operation
- ✓ Low residue formation for increased machine efficiency and lower cleaning costs
- ✓ Synthetic base has a high degree of thermal stability and extremely low boil-off, resulting in very economical consumption

### Properties

- ✓ Widely used on IS and AIS machines
- ✓ NSF H2-registered
- ✓ SO 21469, Kosher- and Halal-certified

### Application area

- ✓ For high-temperature lubrication, specially developed and proven for lubrication of hollow glass machines:
- ✓ For lubrication points in central lubrication systems (e.g. Lincoln etc.)
- ✓ For lubricating machines and springs used in the normal and high temperature ranges
- ✓ Excellent high-temperature oil for the glass, ceramic, enamel and food industries

### Instructions

Observe the machine manufacturer's specifications. Application via drip oiler, central lubrication systems, oil spray systems or by hand.

H2 products must not be used in areas where foodstuffs are manufactured. H2 products can be used as lubricants, release agents or anti-corrosion agents for machine parts and equipment provided that they do not come into contact with foodstuffs.

Product Description	Contents	Weight of content	Gross weight	Article Number	Packaging Unit
TUNFLUID HTG 220	1000 l	953 kg	1023 kg	1106148	1 PCS



Technical Product Data	TUNFLUID HTG 220
Density/conditions	0.953 g/cm <sup>3</sup> / at 20°C
Colour spectrum	Transparent Yellowish
Oil basis	Ester
Kinematic viscosity / condition	220 mm <sup>2</sup> /s / at 40°C
Min. flashing point / conditions	> 250°C / nach ISO 2592
Pour point	-40 °C
Min./max. temperature conditions	-35 to 250 °C

The information provided here is based on our general technical experience and knowledge related to printing. All specifications are guidelines based on product design, the specified use and mechanical and systems engineering. But the information does not represent any pledge about features or any assurance about the product's suitability for use in a particular case. The user is not released from the responsibility of testing the product.

Depending on the mechanical, dynamic, chemical and thermal stresses to which they are subjected, lubricants alter their technical values on a pressure- and time-dependent basis. The changes can have an impact on the function in the application.

TUNAP products are continuously refined. We reserve the right to change all technical data in this document at any time and without any prior notification. Obligations of any kind are in no way implied.