## **Product Information**



## **TUNGREASE CP-00/50**

Dynamically light and fully synthetic H1 high-performance fluid grease with high levels of wear resistance and corrosion protection

#### Benefits

- Outstanding pressure rating for optimal wear protection and longer component and machine service life
- Extremely high level of water resistance and outstanding corrosion protection ensure reliable lubrication even under adverse conditions and in outdoor applications
- ✓ Versatile high-performance lubricating grease to help reduce the number of products required
- The very soft consistency in line with NLGI 00 means that the product can be easily delivered by lubricating units

### **Properties**

- An especially pressure-resistant high-performance grease suitable for a wide range of applications
- Specially developed combination of synthetic base oils, CaSuX thickener and additives to protect against wear, oxidation and corrosion
- ✓ NSF H1 registered
- ✓ ISO 21469, Kosher and Halal certified

### Application area

- Special lubricating grease for use in the following applications: Loaded roller and slide bearings, joints and other sliding pairs in machines and plants, e.g. in filling stations, autoclaves, diverter wheels, fans, kilns
- Linear guides and drives
- For all applications for which water resistance, an extended temperature range and/or high loads are decisive, or which are subject to special regulations that require the use of non-critical lubricants.
- ✓ In accordance with strict standards on the use of lubricants in the food, drink and pharmaceutical industries

#### Instructions

In accordance with technological standards for lubricating greases.

We recommend cleaning the surfaces to be lubricated beforehand with a suitable cleaner (TUNCLEAN 895, FDB or EL) and leaving to dry. If the product is to be used in the food processing industry: Only the minimum quantity technically necessary may be used.

If the product is used as a corrosion-protection film for the food processing industry, it must be completely removed before the device in question is used again.

Product Description	Contents	Weight of content	Gross weight	Article Number	Packaging Unit
TUNGREASE CP-00/50	0 ml	1 kg	1.25 kg	1107569	10 PCS

The information provided here is based on our general technical experience and knowledge related to printing. All specifications are guidelines based on product design, the specified use and mechanical and systems engineering. But the information does not represent any pledge about features or any assurance about the product's suitability for use in a particular case. The user is not released from the responsibility of testing the product.

PI 20250106

# **Product Information**





Technical Product Data	TUNGREASE CP-00/50
Density/conditions	0.89 g/cm <sup>3</sup> / at 20°C
Colour spectrum	Beige
Oil basis	Synthetic
Thickener	Calcium sulfonate complex soap
Base oil viscosity, kinematic/conditions	46 mm <sup>2</sup> /s / at 40°C
NLGI grade/conditions	00 / with DIN 51818
Behaviour in the presence of water/conditions	≤ 1 / nach DIN 51807-1
Corrosion rating EMCOR, dist. Water/con-	≤ 1 / nach DIN 51802, SKF Emcor-Test
ditions	2 17 Hach Bitt 51002, Six Efficit lest
Rating copper corrosion/conditions	1 / nach 24h bei 100°C, nach DIN 51811
VKA welding load/conditions	3400 N / in accordance with DIN 51350-4, VKA test (Institute for Internal Combustion Engines)
Four-ball test, wear mark at 1h/150N/conditions	≤ 0,4 mm / nach DIN 51350-3, VKA-Test
Four-ball test, wear mark at 1h/300N/ conditions	≤ 0,4 mm / nach DIN 51350-3, VKA-Test
Four-ball test, wear mark at 1min/1000N/conditions	≤ 0,5 mm / nach DIN 51350-2, VKA-Test
Min./max. temperature conditions	-40 to 140 °C