

## TUNFLUID TAC 2000

Fully synthetic adhesive lubricant for the food processing industry

### Benefits

- ✓ Precise aerosol application with excellent adhesive properties
- ✓ Water-resistant
- ✓ Optimal protection against wear and corrosion
- ✓ High creep effect
- ✓ High operational safety even under extreme conditions

### Properties

- ✓ Versatile multi-purpose oil with very good wear and corrosion protection
- ✓ NSF H1-registered
- ✓ ISO 21469, Kosher- and Halal-certified
- ✓ Colourless, transparent, non-discolouring

### Application area

- ✓ For lubricating chains, ropes, open gear drives, levers, joints, linkages, hinges, sliding points and bearings for which there is a danger of direct contact between the lubricant and foodstuffs:
- ✓ Filling machines, packaging machines, sealing machines
- ✓ Chains and conveyors
- ✓ Gears
- ✓ Joints, pistons, guides, tube tracks
- ✓ Plain and roller bearings

### Instructions

Pre-clean the surface to be treated. From a distance of approx. 20 cm, spray an even coat. Observe the applicable safety regulations.

If the product is to be used in the food processing industry: Only the minimum quantity technically necessary may be used. If the product is to be used as an anti-corrosive film for surfaces in contact with food, it must be completely removed before the device in question is used again.

Product Description	Contents	Weight of content	Gross weight	Article Number	Packaging Unit
TUNFLUID TAC 2000	500 ml	0.35 kg	0.479 kg	11AC14224A0500	12 PCS





Technical Product Data	TUNFLUID TAC 2000
Density/conditions	0.816 g/cm <sup>3</sup> / at 20°C
Colour spectrum	Colourless Clear
Oil basis	Synthetic
Kinematic viscosity / condition	2000 mm <sup>2</sup> /s / at 40°C
Flow time (4mm- Ford cup)/conditions	17.5 s / in accordance with DIN EN ISO 2431
Min. flashing point /conditions	200 / in accordance with ISO 2592
Pour point	-6 °C

The information provided here is based on our general technical experience and knowledge related to printing. All specifications are guidelines based on product design, the specified use and mechanical and systems engineering. But the information does not represent any pledge about features or any assurance about the product's suitability for use in a particular case. The user is not released from the responsibility of testing the product.

Depending on the mechanical, dynamic, chemical and thermal stresses to which they are subjected, lubricants alter their technical values on a pressure- and time-dependent basis. The changes can have an impact on the function in the application.

TUNAP products are continuously refined. We reserve the right to change all technical data in this document at any time and without any prior notification. Obligations of any kind are in no way implied.