

TUNGEAR H1-320

Fully synthetic gear and hydraulic oil for the food processing industry

Benefits

- ✓ Reliable operation due to a high level of protection against seizing (LS \geq 12) and micro-pitting (GFT agent)
- ✓ Extended oil change intervals due to higher thermal stability of synthetic base oil compared to mineral-oil-based gear oils
- ✓ NSF H1-registered for increased product and process reliability
- ✓ Gear oils in the TUNGEAR H1 range are based on synthetic oils, have excellent lubrication performance and feature wear, oxidation and corrosion inhibitors

Properties

- ✓ NSF H1-registered
- ✓ ISO 21469, Kosher- and Halal-certified
- ✓ Excellent corrosion protection, resistant to ageing and shearing
- ✓ Reduces friction and wear
- ✓ High pressure rating
- ✓ Reduces running noises and vibrations
- ✓ High viscosity index

Application area

- ✓ Food manufacturing and processing industry:
- ✓ Bakeries, bread factories, dairies, abattoirs, meat factories, animal farms, beverage and packaging industries
- ✓ High-pressure hydraulic systems
- ✓ Gears, especially under extreme conditions such as high or low temperatures and large sliding contact area, high surface pressure and shock loads
- ✓ Plain and roller bearings, spindles, guides, cams, universal joints
- ✓ Compressors

Instructions

Gearbox oils in the TUNGEAR H1 range must be used in accordance with the requirements of the gear and/or system manufacturer. Application via oiler, oil can, brush or central lubrication unit.

If the product is to be used in the food processing industry: Only the minimum quantity technically necessary may be used. If the product is to be used as an anti-corrosive film for surfaces in contact with food, it must be completely removed before the device in question is used again.

Product Description	Contents	Weight of content	Gross weight	Article Number	Packaging Unit
TUNGEAR H1-320	20 l	16.7 kg	18.5 kg	11AC117053L0200	1 PCS



Technical Product Data	TUNGEAR H1-320
Density/conditions	0.852 g/cm ³ / at 20°C
Colour spectrum	Colourless Light yellow
Oil basis	PAO Polyalphaolefin PAO-Polyalphaolefin
Rating copper corrosion/conditions	1-100 / after 24h at 100°C, nach DIN 51811
Scuffing test (FZG)/conditions	12 / in accordance with DIN ISO 14635-1
Min. flashing point /conditions	250 / in accordance with ISO 2592
Pour point	-40 °C
Min./max. temperature conditions	-30 to 120 °C